

Film thickness decreases with maintaining shape because of surface membrane.

Protuberant is remained in surrounding part.

Thermoplastic resin paste (print paste is high molecular weight resin solution)

Film thickness decreases due to curing-shrinkage.

There becomes almost no protuberant in surrounding part.

Thermosetting resin paste (print paste is low molecular weight resin precursor)